

ARCHCO 453HT EPOXY CAULK

Heat Resistant Coating Epoxy-Phenolic Novolac Caulk

Description

Archco 453 HT Caulk is an ultra-high solids, fast curing, technologically advanced epoxy-phenolic novolac caulk. It is specifically designed to handle the harsh environments in the petroleum industry, including all petroleum crudes. It is an excellent caulking material to use with internal pipeline sleeves with high operating temperatures. It combines excellent heat resistance with outstanding corrosion protection. Archco 453 HT resists immersion temperatures up to 325°F (163°C) for many applications and higher temperatures in non-immersion service.

Uses

Sealing steel or concrete transitions in storage tanks, tubular pipes, casing exteriors, interior and exterior pipes, floors, tank pads, trenches, troughs, sumps and pits.

Features

- Excellent adhesion
- High temperature stability
- Abrasion and impact resistance
- High temperature water resistances, oil & gas
- Thermal and mechanical shock resistance
- Excellent flexibility
- Resists wide range of chemicals, produced water, sea water

Application

All surfaces must be clean and dry, free of dust, dirt, oil or other foreign matter. Steel surfaces shall be abrasive blasted to SSPC 10 near white finish with a minimum of 3-5 mil (76-127 microns) angular profile for best results. Concrete shall be abrasive blasted or etched with 10% muriatic acid. Use of a primer is required for concrete to improve adhesion and minimize outgassing. See a Premier Coatings representative for additional information.

This product is supplied in cartridge form. Application equipment is normally a two component cartridge gun in combination with a static mixer tip. The cartridge gun may be manual or air-assisted. Keep in mind that the first material exiting the static mixing tip will likely be off-ratio and should be discarded. The static mixing tip may be omitted, but the material must be thoroughly mixed prior to use. This is normally accomplished using a wooden stir stick. Application of the caulk may be accomplished directly from the gun using the mixing tip or with a trowel or other tool with a wide, flat blade. Any variation in product color during application will indicate the product is off-ratio.

Consult Premier Coatings representative for more information.



Archco 453HT Epoxy Caulk

TECHNICAL DATA

PROPERTIES	VALUE
Solids Content by Volume	98 - 100%
Minimum Dewpoint / Substrate Differential	Dewpoint +5°F (+3°C)
Minimum Substrate Temperature	60°F (16°C)
Minimum Ambient Temperature	60°F (16°C)
Mixing Ratio (A/B) by Volume	4:1
Recommended Thickness	10 - 250 mils DFT (254 - 6350 microns DFT)
Theoretical Coverage	
@ 1 mil dry (0.02 mm)	1604 sq. ft. per gallon (39.4 sq. m. per liter)
@ 20 mil dry (0.50 mm)	80 sq. ft. per gallon (2.0 sq. m. per liter)
@ 40 mil dry (1.02 mm)	40 sq. ft. per gallon (1.0 sq. m. per liter)
Minimum Dry Time @ 77°F (25°C) & 50% Relative Humidity (ASTM D 1640)	
To Touch	1 Hour
To Handle	2 - 3 Hours
To Recoat	3 Hours
Maximum Recoat Time	6 Hours
Cure for Immersion (Shore D 75 - 80) @ 77°F (25°C)	12 hours
Flash Point	>200°F (93°C)
Hardness	(Shore D min.): 80
Temperature Resistance*	
Dry Heat	400°F (204°C)
Short Term	700°F (371°C)
Pot Life @ 72°F (22°C)	30 mins.
Color	Tan
VOC	0.12 lbs/gal (14 g/l)

*Note: Continuous immersion temperature resistance is dependent on particular reagent exposure. Consult a Premier Coatings representative.

STORAGE: Minimum 24 months when stored in original containers @ 65°F (18°C) to 85°F (30°C).

CLEANING: Clean equipment with MEK or equivalent solvent cleaner, such as Archco 400E Thinner.

HEALTH AND SAFETY: Wear protective clothing and ensure adequate ventilation. Avoid contact with skin and eyes. See material safety data sheet for further information.

PACKAGING: 50 ml and 375 ml dual cartridges.

Dispensing guns and static mixing tips (50 ml or 325 ml) sold separately.



HOUSTON:
9747 Whithorn Drive,
Houston, Texas,
U.S.A. 77095
Tel: 1-281-821-3355
Fax: 1-281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 1-416-291-3435
Fax: 1-416-291-0898

e-mail: info@premiercoatings.com

www.premiercoatings.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.