

ARCHCO 15™

High Build Flexible Water Based Acrylic Topcoat

Description

Archco 15 is a single part, high build, high performance water based acrylic topcoat for Premier Coatings Tape Systems.

Uses

Developed to be used as a topcoat over Premier Coatings Petrolatum Tapes, Premcote FB-30™ Tape, and Premcote Glass Outerwrap™.

Features

- Single component
- Environmentally friendly
- Can be applied by brush or spray
- Flexible
- Cures at temperatures down to 50°F (10°C)
- Fast dry

Application

Surface to be top coated shall be clean, dry and free of any dust or foreign matter.

Brush Applications: Archco 15 can be applied immediately after application of the Premier Coatings Systems. Archco 15 shall be applied in two coats consisting of 18 to 23 mils (457 - 584 microns) wet-film thickness per coat. Recoat time is approximately 1 to 2 hours at 77°F (25°C).

Spray Applications: An equivalent to a Graco 56:1 airless with 3/8" (9.5 mm) hose with a tip size of 0.031" to .035" (0.8 to 0.9 mm) shall be used. Archco 15 shall be applied in two coats consisting of 18 to 23 mils (457 - 584 microns) wet-film thickness per coat. Recoat time is approximately 1 to 2 hours at 77°F (25°C).

Archco 15™

TECHNICAL DATA

PROPERTIES	VALUE
Solids by Weight	55%
Weight	10.71 lbs/gal (1.28 kg/L)
Flash Point	144°F (62°C)
VOC's	0.36 lbs/gal (43 grams/liter)
Viscosity @ 77°F (25°C)	Brookfield #6 spindle 10 rpm – 36,500 cP 100 rpm – 6,000 cP
Recommended Dry Film Thickness	10 to 12 mils (254 - 305 microns) per coat x 2 coats
Recommended Wet Film Thickness	18 to 20 mils (457 - 508 microns) per coat x 2 coats
Application Temperature	50°F (25°C) to 130°F (54°C)
Color	Black or White
Theoretical Coverage	44 SF/Gal @ 20 mils DFT(4 SQM/L @508 microns)

STORAGE AND HANDLING:

Minimum 2 years when stored in original containers
@ 50°F (25°C) to 105°F (41°C).

CLEANING:

Clean equipment with soap and water

PACKAGING:

5 gallon container
(19 liter container)

HEALTH AND SAFETY:

Wear suitable protective clothing and glasses.
See Safety Data Sheets (SDS).



HOUSTON:
9710 Telge Road,
Houston, Texas,
U.S.A. 77095
Tel: 1-281-821-3355
Fax: 1-281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 1-416-291-3435
Fax: 1-416-291-0898

e-mail: info@premiercoatings.com

www.premiercoatings.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.