

PREMIER POLY-WRAP HD

High Performance Outerwrap and Compression Film

Description

Premier Poly-Wrap HD is a 300 gauge (3.0 mil) wrap made from high performance metallocene resins.

Uses

Use as a compression film for Premcote Glass Outerwrap. It is also used as an protective layer over Premier Petrolatum Tape Systems.

Features

- Superior holding force
- Excellent Prestretch with no film breaks
- Excellent Puncture resistant
- Aggressive cling to self
- Uses maximum performance metallocene resins
- Excellent conformability

Application

The Poly-Wrap HD shall be spirally wrapped using sufficient to wrap over the Premcote Glass Outerwrap and Premier Petrolatum Tape System.



Premier Poly-Wrap HD

PROPERTY SPECIFICATIONS

PROPERTIES	ENGLISH	METRIC
Yield	7,495 sq. in/lb	10.66 sq. m/kg
Ultimate Tensile MD (ASTM D 882-90)	4,300 psi	29,647 KPa
Ultimate Tensile TD (Method A)	3,850 psi	26,545 KPa
Elongation at Break MD (ASTM D 882-90)	350%	350%
Elongation at Break TD (Method A)	375%	375%
Graves Tear MD (ASTM D 882-90)	210 g/mil	210 g/mil
Graves Tear TD (Method A)	195 g/mil	195 g/mil
Elmendorf Tear MD (ASTM D 882-90)	155 g/mil	155 g/mil
Elmendorf Tear TD (Method A)	215 g/mil	215 g/mil
Impact Strength		
Drop height by @77°F	70 inches	1,778 mm
Falling ball @ 0°F	70 inches	1,778 mm
1" dia./66g @ -20°F	70 inches	1,778 mm
Haze Gardner (ASTM D 1003)	0.6%	0.6%
MVTR (WVTR) (ASTM F 1249 100°F, 100% RH)	8.5 g/100 sq. in/24hr	8.5 g/64,516 sq. mm/24hr
Thickness	3.0 mils	76 microns
Roll Widths	4", 6" and 12"	100 mm, 150 mm and 300 mm
Roll Lengths	250 ft.	62.5 m

Quantity Estimates

Tape Width	Rolls*/ Case	Coverage with 50% Overlap
in.	ea.	ea.
4" (100 mm)	6	275 ft ² /case (25.5 m ² /case)
6" (150 mm)	4	275 ft ² /case (25.5 m ² /case)
12" (300 mm)	2	275 ft ² /case (25.5 m ² /case)

*All rolls 250 feet (62.5 m) in length



HOUSTON:
9710 Telge Road,
Houston, Texas,
U.S.A. 77095
Tel: 1-281-821-3355
Fax: 1-281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 1-416-291-3435
Fax: 1-416-291-0898

e-mail: info@premiercoatings.com

www.premiercoatings.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.