

PREMIER BASECOAT™ KIT

Saturation Coating for Covercoat System

Description

The Premier Basecoat Kit is a two component durable coating, consisting of a liquid portion containing synthetic polymers and waterproofing admixtures and a cementitious powder portion consisting of fine fillers.

Uses

Premier Basecoat Kit, in conjunction with the Premier D14 Scrim™, is used to provide a tough protective outer coating over Premier Petrolatum Tapes and as the saturation coat for the Premier Coatings Covercoat System™.

Features

- Durable and weatherproof
- Excellent flexibility
- Good resistance to moderate trafficking
- Application by brush or roller

Application

Component A (Gray Powder) is slowly added to Component B (White Liquid) while being thoroughly mixed using a wooden mixing stick or a slow speed drill jiffy mixer. Keep mixing the solution until all the powder has been added and the mixture takes on a smooth slurry texture. The basecoat should be re-mixed every 10-15 minutes to ensure that there is no settling out or separation between the two components. In high ambient temperatures, above 77°F (25°C), repeat mixing every 5 to 7 minutes.

Premier Basecoat™ Kit

TECHNICAL DATA

| PROPERTIES | VALUE |
|-------------------|----------------------------------|
| Specific Gravity | 1.5 |
| Drying Time | 2 hours @ 77°F (25°C) |
| Temperature Range | |
| For Application | 32°F to +122°F (0°C to +50°C) |
| For Service | -22°F to +140°F (-30°C to +60°C) |
| Spread Rate | 225 sf/case (21 sq mt. / case) |

PACKAGING:

1 case contains the following: 2 each - 3 lb. bags of Part A (Powder) & 2 each - 0.25 gals of Part B (Liquid).

STORAGE AND HANDLING:

Store in original containers in a cool, dry place away from any sources of ignition. Recommended shelf life: 12 months.

HEALTH AND SAFETY:

Normal hygiene procedures. Wash hands thoroughly with soap and water or a proprietary hand-cleaner prior to eating. Launder contaminated clothing, gloves, etc. See safety data sheet for further information.



HOUSTON:

9710 Telge Road,
Houston, Texas,
U.S.A. 77095
Tel: 1-281-821-3355
Fax: 1-281-821-0304

TORONTO:

90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 1-416-291-3435
Fax: 1-416-291-0898

e-mail: info@premiercoatings.com

www.premiercoatings.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.